WHAT IS CLAIMED IS:

1. A storage-stable, liquid, partially trimerized and allophanized polyisocyanate having an NCO group content of 15 to 41% by weight, and comprising the partial trimerization and allophanation product of: 5 from 5 to 85% by weight of toluene diisocyanate (A) having an isomer distribution of: (1) from 60 to 100% by weight of the 2,4-isomer, and (2) from 0 to 40% by weight of the 2,6-isomer, with 10 the sum of the %'s by weight of (A)(1) and (A)(2) totaling 100% by weight of (A); and (B) from 5 to 85% by weight of a polyisocyanate of the diphenylmethane series comprising from: 15 **(1)** 0 to 50% by weight of higher functionality polyisocyanates of the diphenylmethane series, (2) 40 to 100% by weight of 4,4'-diphenylmethane diisocyanate, (3) 0 to 20% by weight of 2,4'-diphenylmethane 20 diisocyanate, and (4) 0 to 6% by weight of 2,2'-diphenylmethane diisocyanate, with the sum of the %'s by weight of (B)(1), (B)(2), 25 (B)(3) and (B)(4) totaling 100% by weight of (B): and (C) from 0.1 to 10% by weight of an organic compound or mixture thereof containing from 1 to 4 hydroxyl groups capable of reacting with NCO groups and having a 30 molecular weight of from 32 to 6000

wherein the sum of the %'s by weight of (A), (B) and (C) total 100% by weight.

- 2. A storage-stable, liquid, partially trimerized and allophanized polyisocyanate according to Claim 1, wherein the storage-stable, liquid, partially trimerized polyisocyanate composition has an NCO group content of about 17 to about 39% by weight, and comprises:
 - (A) from 10 to 80% by weight of toluene diisocyanate having an isomer distribution of:
 - (1) from 60 to 100% by weight of the 2,4-isomer, and
 - (2) from 0 to 40% by weight of the 2,6-isomer, with the sum of the %'s by weight of (A)(1) and (A)(2) totaling 100% by weight of (A):

and

15

- (B) from 10 to 80% by weight of a polyisocyanate of the diphenylmethane series comprising from:
 - (1) 0 to 50% by weight of higher functionality polyisocyanates of the diphenylmethane series,
 - (2) 40 to 100% by weight of 4,4'-diphenylmethane diisocyanate,
 - (3) 0 to 20% by weight of 2,4'-diphenylmethane diisocyanate,

and

(4)

0 to 6% by weight of 2,2'-diphenylmethane diisocyanate,

with the sum of the %'s by weight of (B)(1), (B)(2), (B)(3) and (B)(4) totaling 100% by weight of (B):

and

30

(C) from 0.1 to 10% by weight of an organic compound or mixture thereof containing from 1 to 4 hydroxyl groups

10

5

20

capable of reacting with NCO groups and having a molecular weight of from 32 to 6000;

wherein the sum of the %'s by weight of (A), (B) and (C) total 100% by weight.

- 5 3. A storage-stable, liquid, partially trimerized and allophanized polyisocyanate according to Claim 1, wherein (C) is an aliphatic alcohol having from 1 to 36 carbon atoms or an aromatic alcohol having from 5 to 20 carbon atoms.
- A storage-stable, liquid, partially trimerized and allophanized polyisocyanate according to Claim 3, wherein (C) is chosen from at least one of methanol, ethanol, 1,2-ethanediol, 1-propanol, 2-propanol, 1-butanol, isobutyl alcohol, 2-butanol, n-amyl alcohol, sec-amyl alcohol, tert-amyl alcohol, 1-ethyl-1-propanol, n-hexanol and isomers thereof, n-octyl alcohol, 2-octyl alcohol, 2-ethyl-1-hexanol, n-decyl alcohol, n-dodecyl alcohol, neopentylglycol, n-tetradecyl alcohol, n-hexadecyl alcohol, n-octadecyl alcohol, 1,2 and 1,3-propanediol, 1,4-butanediol, 1,3-butanediol, 2,3-butanediol, 3-methyl-2-butanol, 3,3-dimethyl-1-butanol, 2-ethyl-1,3-hexanediol, glycerol, 1,2,4-butanetriol, pentaerythritol, diethylene glycol, dipropylene glycol, diethylene glycol, triethylene glycol and phenol.
 - 5. A storage-stable, liquid, partially trimerized and allophanized polyisocyanate according to Claim 4, wherein (C) is isobutyl alcohol.
 - 6. A process for the preparation of a storage-stable, liquid, partially trimerized and allophanized polyisocyanate composition containing isocyanurate groups and having an NCO group content of about 41% by weight, comprising:
 - (1) partially trimerizing and allophanizing:
 - (A) from 5 to 85% by weight of toluene diisocyanate having an isomer distribution of:
 - (1) from 60 to 100% by weight of the 2,4-isomer, and

30

20

(2)

followed by the addition of:

an acidic stopper.

(D)

from 0 to 40% by weight of the 2,6-isomer, with the sum of the %'s by weight of (A)(1) and (A)(2) totaling 100% by weight of (A); and 5 from 5 to 85% by weight of a polyisocyanate of the (B) diphenylmethane series comprising from: 0 to 50% by weight of higher functionality (1) polyisocyanates of the diphenylmethane series. (2) 40 to 100% by weight of 4,4'-diphenylmethane 10 diisocyanate, (3) 0 to 20% by weight of 2,4'-diphenylmethane diisocyanate, and (4) 0 to 6% by weight of 2,2'-diphenylmethane 15 diisocyanate. with the sum of the %'s by weight of (B)(1), (B)(2), (B)(3) and (B)(4) totaling 100% by weight of (B); and (C) from 0.1 to 10% by weight of an organic compound or 20 mixture thereof containing from 1 to 4 hydroxyl groups capable of reacting with NCO groups and having a molecular weight of from 32 to 6000; wherein the sum of the %'s by weight of (A), (B) and (C) total 100% by weight. 25 in the presence of: at least one trimerization catalyst and optionally at least one (C) allophanation catalyst,

5

10

15

20

25

30

7. The process of Claim 6, wherein the storage-stable, liquid, partially trimerized and allophanized polyisocyanate composition has an NCO group content of about 17 to about 39% by weight, and comprises: (A) from 10 to 80% by weight of toluene diisocvanate having an isomer distribution of: (1) from 60 to 100% by weight of the 2,4-isomer, and (2) from 0 to 40% by weight of the 2,6-isomer, with the sum of the %'s by weight of (A)(1) and (A)(2) totaling 100% by weight of (A); and (B) from 10 to 80% by weight of a polyisocyanate of the diphenylmethane series comprising from: (1) 0 to 50% by weight of higher functionality polyisocyanates of the diphenylmethane series. (2) 40 to 100% by weight of 4,4'-diphenylmethane diisocyanate, 0 to 20% by weight of 2,4'-diphenylmethane (3) diisocyanate, and (4) 0 to 6% by weight of 2,2'-diphenylmethane diisocyanate, with the sum of the %'s by weight of (B)(1), (B)(2), (B)(3) and (B)(4) totaling 100% by weight of (B); and (C) from 0.1 to 10% by weight of an organic compound or mixture thereof containing from 1 to 4 hydroxyl groups capable of reacting with NCO groups and having a molecular weight of from 32 to 6000 wherein the sum of the %'s by weight of (A), (B) and (C) total 100% by weight.

- 8. A process according to Claim 6, wherein (C) is an aliphatic alcohol having from 1 to 36 carbon atoms or an aromatic alcohol having from 5 to 20 carbon atoms.
- 9. A process according to Claim 8, wherein (C) is chosen from at least one of methanol, ethanol, 1,2-ethanediol, 1-propanol, 2-propanol, 1-butanol, isobutyl alcohol, 2-butanol, n-amyl alcohol, sec-amyl alcohol, tert-amyl alcohol, 1-ethyl-1-propanol, n-hexanol and isomers thereof, n-octyl alcohol, 2-octyl alcohol, 2-ethyl-1-hexanol, n-decyl alcohol, n-dodecyl alcohol, neopentylglycol, n-tetradecyl alcohol, n-hexadecyl alcohol, n-octadecyl alcohol, 1,2 and 1,3-propanediol, 1,4-butanediol, 1,3-butanediol, 2,3-butanediol, 3-methyl-2-butanol, 3,3-dimethyl-1-butanol, 2-ethyl-1,3-hexanediol, glycerol, 1,2,4-butanetriol, pentaerythritol, diethylene glycol, dipropylene glycol, diethylene glycol, triethylene glycol and phenol.
- 10. A process according to Claim 9, wherein (C) is isobutyl 15 alcohol.
 - 11. A storage-stable, liquid prepolymer containing a mixed trimer and allophanate of toluene diisocyanate, a polyisocyanate of the diphenylmethane series and an organic compound, having an NCO group content of about 8 to about 39%, and comprising the reaction product of:
- 20 (I) the liquid, partially trimerized and allophanized polyisocyanate of Claim 1, and
 - (II) an organic component containing from about 1.5 to about 4 hydroxyl groups which are capable of reacting with NCO groups, and having a molecular weight of from about 76 to about 6,000.
 - 12. The storage-stable, liquid prepolymer of Claim 11, wherein (II) said organic component contains from about 1.8 to 3 hydroxyl groups and has an molecular weight of about 76 to about 4,800.
- 13. The storage-stable, liquid prepolymer of Claim 11, wherein30 (II) said organic component comprises a polyether polyol having an

equivalent weight of at least about 900 and containing at least about 10% by weight of ethylene oxide, based on 100% by weight of alkylene oxide.

- 14. The storage-stable, liquid prepolymer of Claim 11, wherein the NCO group content is from about 20 to about 35%.
- 15. A process for the production of a storage-stable, liquid prepolymer having an NCO group content of about 8 to about 39%, containing a mixed trimer and allophanate of toluene diisocyanate, a polyisocyanate of the diphenylmethane series and an organic compound, comprising:

10 reacting

5

15

20

25

30

(I) the liquid, partially trimerized polyisocyanate produced by the process of Claim 6,

with

- (II) an organic component containing from about 1.5 to about 4 hydroxyl groups which are capable of reacting with NCO groups and having a molecular weight of from about 76 to about 6,000.
- 16. The process of Claim 15, wherein (II) said organic component contains from about 1.8 to about 3 hydroxyl groups and has a molecular weight of about 76 to about 4,800.
- 17. The process of Claim 16, wherein (II) said organic component comprises a polyether polyol having an equivalent weight of at least about 900 and containing at least about 10% by weight of ethylene oxide, based on 100% by weight of alkylene oxide.
- 18. The process of Claim 15, wherein the NCO group content is from about 20 to about 35%.
- 19. A process for preparing a storage-stable, liquid, partially trimerized and allophanized polyisocyanate composition containing isocyanurate groups and having an NCO group content of about 15 to about 41% by weight, comprising:
- (1) partially trimerizing and allophanizing:

| | (4 | A) fro | from 5 to 85% by weight of toluene diisocyanate having an isomer distribution of: | | |
|----|---|--------|--|--|--|
| | | ha | | | |
| | | (1) | from 60 to 100% by weight of the 2,4-isomer, | | |
| | | an | d . | | |
| 5 | | (2) | from 0 to 40% by weight of the 2,6-isomer, with | | |
| | | | the sum of the %'s by weight of (A)(1) and | | |
| | | | (A)(2) totaling 100% by weight of (A); | | |
| | aı | nd | | | |
| | (E | 3) fro | m 5 to 85% by weight of a polyisocyanate of the | | |
| 10 | | dip | henylmethane series comprising from: | | |
| | | (1) | 0 to 50% by weight of higher functionality | | |
| | | | polyisocyanates of the diphenylmethane series, | | |
| | | (2) | 40 to 100% by weight of 4,4'-diphenylmethane | | |
| | | | diisocyanate, | | |
| 15 | | (3) | 0 to 20% by weight of 2,4'-diphenylmethane | | |
| | | | diisocyanate, | | |
| | | and | . | | |
| | | (4) | 0 to 6% by weight of 2,2'-diphenylmethane | | |
| | | | diisocyanate, | | |
| 20 | with the sum of the %'s by weight of (B)(1), (B)(2), | | | | |
| | | (B) | (3) and (B)(4) totaling 100% by weight of (B); | | |
| | an | nd | | | |
| | (C |) fror | from 0.1 to 10% by weight of an organic compound or mixture thereof containing from 1 to 4 hydroxyl groups | | |
| | | mix | | | |
| 25 | | cap | able of reacting with NCO groups and having a | | |
| | | mo | molecular weight of from 32 to 6000; | | |
| | wherein the sum of the %'s by weight of (A), (B) and (C) total | | | | |
| | 100% by weight. | | | | |
| | in the presence of: | | | | |
| 30 | (C) at least one trimerization catalyst and optionally at least one | | | | |
| | allophanation catalyst, followed by the addition of: | | | | |
| | | | | | |
| | | | | | |

- (D) an acidic stopper; and
- (2) blending
 - (E) a polyisocyanate of the diphenylmethane series comprised from:
- 5 (1) 0 to 50% by weight of higher functionality polyisocyanates of the diphenylmethane series,
 - (2) 30 to 60% by weight of 4,4'-MDI,
 - (3) 3 to 60% by weight of 2,4'-MDI; and
 - (4) 0 to 6% by weight of 2,2'-MDI; or
- 10 (F) a uretonimine modified polyisocyanates of the diphenylmethane series comprised from:
 - (1) 34 to 100% by weight of 4,4'-MDI,
 - (2) 0 to 60% by weight of 2,4'-MDI, and
 - (3) 0 to 6% by weight of 2,2'-MDI.